


**MYK LATICRETE**

## 303 Floor and Wall Tile Adhesive



Polymer based economy adhesive for fixing ceramic tiles and small format natural stone on dry areas of interior floors & walls

### Features / Benefits

- Single component, just add water
- Interior applications, polymer based
- Economical solution for economical ceramic tiles
- Bonds to various substrates
- Complies with EN / ISO with a C1T classification.
- Exceeds IS 15477:2019 – Type 1T Adhesive standards.

### Substrates

- Concrete
- Concrete Masonry
- Cement Mortar Beds
- Cement Plaster
- Ceramic Tile\*
- Brick Masonry
- Cement Terrazzo
- Existing Natural Stone\*

\* Surface to be cleaned and roughened before installation of tiles or stones.

### Application

MYK LATICRETE 303 is a single-component polymer based economy adhesive ideal for interior applications, particularly for fixing ceramic tiles and small format natural stones on various cement-based substrates. Can be used up to maximum 12 mm bed thickness.

### Certifications

IS 15477:2019 Type: 1T

EN / ISO: C1T



## PERFORMANCE PROPERTIES

303 Adhesive mixed with Water

### Applicable Standards:

EN 12004 & ISO 13007; IS15477:2019

EN / ISO Data		
Property: Test Method	Requirement	Typical Values
Open Time: EN 1346	$\geq 0.50$ N/mm <sup>2</sup>	0.65 – 0.69 N/mm <sup>2</sup>
Slip Resistance: EN 1308	$\leq 0.50$ mm	0.40-0.45 mm
<b>Tensile Adhesion Strength</b>		
Initial: EN 1348 – Clause 8.2	$\geq 0.50$ N/mm <sup>2</sup>	0.50 – 0.55 N/mm <sup>2</sup>
After Water Immersion: EN 1348 - Clause 8.3	$\geq 0.50$ N/mm <sup>2</sup>	0.50 – 0.55 N/mm <sup>2</sup>
Heat Ageing: EN 1348 – Clause 8.4	$\geq 0.50$ N/mm <sup>2</sup>	0.50 – 0.55 N/mm <sup>2</sup>
Freeze- Thaw: EN 1348 – Clause 8.5	$\geq 0.50$ N/mm <sup>2</sup>	0.50 – 0.55 N/mm <sup>2</sup>

The adhesive mortar conforms to EN12004 / ISO 13007 as C1T

IS Data		
Property: Test method	Requirement	Typical Values
<b>Tensile Adhesion</b>		
Dry Condition – Annex A (Clause 5.1)	Minimum 0.50 N/mm <sup>2</sup>	0.55-0.65 N/mm <sup>2</sup>
<b>Shear Adhesion</b>		
Dry Condition – Annex B (Clause 5.2)	Minimum 1.00 N/mm <sup>2</sup>	1.05-1.15 N/mm <sup>2</sup>
<b>Slip Resistance</b>		
Slip Resistance – Annex E (Clause 5.5)	$\leq 0.50$ mm	0.25-0.35 mm

The Adhesive mortar conforms to IS 15477: 2019 - Type 1T Adhesive

### Packaging:

20 kg bag

### Colour:

Grey

### Shelf Life:

Factory sealed containers of this product are guaranteed to be of first quality for One (1) year if stored off the ground in a dry area.

. \*High humidity will reduce the shelf life of bagged product

### Coverage:

Approx. 55-60 Sft per 20 Kg pack, using  $1/4 \times 1/4$  (6 mm  $\times$  6 mm) square notched trowel for a bed of 3mm.

Coverage will vary depending on trowel notch size, type and size of tile and substrate smoothness and evenness.

### Working Properties at 70 °F (21 °C)

303 Adhesive mixed with Water

Pot Life	2 - 3 hours
Time to Heavy Traffic	16 - 24 hours

Specifications subject to change without notification. The results shown are typical but reflect test procedures used. Actual field performance will depend on installation methods and site conditions.

## INSTALLATION

### Surface Preparation:

All surfaces should be between 40 °F (4 °C) and 104 °F (40 °C) and structurally sound, clean and free of all dirt, oil, grease, loose peeling paint, laitance, concrete sealers or curing compounds. Check the surface to be true to plumb. All slabs must be plumb and true to within 1/4" (6mm) in 10 ft (3 m). Rough or uneven concrete surfaces should be made smooth with MYK LATICRETE® Screed/Plaster material to provide a wood float (or better) finish.

Dry, dusty concrete slabs or masonry should be dampened, and excess water swept off. Installation may be made on a damp surface. New concrete slabs shall be damp cured and 28\* days old before application.

\*No minimum cure time for concrete slabs when thin-set mortar is mixed with latex additive.

Expansion joints shall be provided through the tile work from all construction or expansion joints in the substrate. Do not cover expansion joints with

thin set mortar. Follow ANSI Specification AN-3.8 "Requirements for Expansion Joints" or TCA Detail EJ171 "Expansion Joints". For tile installation over the Cement Backer Board: follow TCA installation details W244.

**NOTE:** For tile or stone installations on plywood and wood substrates, DWA 215 OR DWA 215 PLUS OR PUA 212 is recommended. Please refer specific product Technical Data Sheet for detailed recommendations.

#### **Mixing:**

Place clean, potable water into a clean mixing bowl. Add 303 powder into the mixing bowl. Use approximately 4.2 – 4.8 L of water for 20 kg of powder.

Mix by hand or with a slow speed mixer to a smooth, trowelable consistency. Allow the adhesive to slake for 5 minutes. Adjust consistency if necessary. Remix and apply with the proper sized notched trowel.

**Note:** Addition of LATICRETE® latex admix\*, partially or completely replacing water would enhance the bond strength, flexibility of the thinset mortar.

\* Contact MYK LATICRETE technical services for large format tile or stone installations on exterior surfaces.

#### **APPLICATION**

Apply adhesive to the substrate with the flat side of the trowel, pressing firmly to work into surface. Comb on additional adhesive with the notched side. Use the proper sized notched trowel to ensure full bedding of the tile. Spread as much adhesive as can be covered with tile in 10 minutes. Back butter large format tiles (> 12"x12") to provide full bedding and firm support. Place tiles into wet, sticky adhesive and beat in using a beating block and rubber mallet to imbed tile and adjust level. Check the adhesive for complete coverage by periodically removing a tile and inspecting bedding adhesive transfer onto back of tile. Use of MYK LATICRETE spacer is recommended to provide grout joints between tiles / stones. The joint width shall be as per the recommendation of architect / engineer.

Remove the spacers when the adhesive is set firm.

If the adhesive is skinned over (not sticky), remove and replace it with fresh adhesive.

For highly absorbent natural stones which may form a wet patch when adhesive is used, it is recommended to use suitable LATICRETE® Impregnating sealers on all sides. LATICRETE® 3642 Latex admix can also be used as a bottom coat for natural stones to prevent or reduce wet patches during installation. Please refer Technical Data Sheets of product intended for use for specific instructions of use

#### **HOT & COLD WEATHER TILING:**

\* Please refer to technical document on Hot & Cold weather tiling

#### **Grouting:**

Grout installation shall commence after a minimum of 24 hours curing time at 70 °F (21° C). Grout with LATICRETE® Sanded or Unsanded Grout mixed with LATICRETE® 1776 Grout Admix Plus.

For maximum stain resistance of Internal spacer joints applications, uses SP-100 Stainfree Grout OR MYK LATICRETE Stellar grout

#### **CUSTOMER CARE**

##### **MYK LATICRETE India Pvt Ltd.**

Plot No. 30/C (Sy.No. 83/1), Orbit Building,  
17th Floor, Tower 1, Knowledge City, TSIC,  
Raidurg, Ranga Reddy Dist., Hyderabad - 500  
081, Telangana, India. (T.S)

Tel: +91-40-6817 3100

Customer Care: cc@myklaticrete.com

Website: www.myklaticrete.com